



QUIET SEAL I

#20-6 Black

An autobody undercoating for application to undercarriage for rust protection and sound deadening. Asphalt base undercoating remains pliable and resists temperature extremes. Sprays evenly and dries completely to a smooth consistency.

Suggested Uses:

Panel & fender undersides
Hoods & decks
Trunk interiors
Section repairs
Weld joints
Rust holes
All chassis parts

Benefits:

Prevents rust, anti-corrosive
Reduces road noise
Reduces lingering odor associated with undercoatings
No sagging
Not effected by heat or cold

Packaging:

| | |
|--------------------------|-----------------------|
| UPC Code | 043281005197 |
| Cans per case | 12 |
| Shipping weight per case | 19.6 lbs. |
| Container | 20 fluid ounce can |
| Label weight | 18 ounces (511 grams) |
| Shipping Classification | ORM-D, UN 1950 |
| Hazard Class | 2.1 |

Properties:

| | |
|-------------------------|-------------------------|
| Flammability | "Extremely Flammable" |
| Flash point | -4F |
| Specific Gravity | 0.85 |
| Solids Content | ~40% |
| VOC content | ~29%, cannot exceed 40% |
| MIR value | ~0.30 |
| HAPs content | 4% |
| Storage Temperature | 40-90F |
| Application Temperature | 50-100F |
| Durability | Very Good |
| Abrasion Resistance | Very Good |
| Heat Resistance | 300° F |
| Gasoline Resistance | No |
| Resin System | Petroleum Asphalt |
| Shelf life | Guaranteed for 2 years |
| Food contact rating | No |

Dry Time*:

| | |
|-----------|------------|
| To touch | 10 minutes |
| To handle | 6 hours |

*At 72° F, 50% humidity,
1.5 mil thickness

Curing/Recoat time is extended with multiple coats and excessively thick coats

Gloss*: Low Lustre, 15-25

*as measured on a 60° gloss meter

Available Colors:

| Part # | Description | UPC Code |
|--------|-------------|----------|
|--------|-------------|----------|