

Can

Photo

Not

Available

MRO COLD GALV PRIMER

1-1445

MRO Cold Galv bonds with iron and steel to stop rust and corrosion. Equal to hot dip galvanizing in durability and protection against the caustic action of salt. Can be used as a primer for most paints and heals itself when scratched. Excellent for recoating or spot-priming weathered galvanized surfaces and repairing areas damaged by welding. The years of protection reduces costs and cuts down on labor.

Suggested Uses:

Vehicle bodies
Storage tanks
Bridges
Railroad equipment
Piping
Trailers
Agricultural equipment

Benefits:

Fast dry
Abrasion resistant
Stops rust creepage
Paintable
Excellent outdoor durability
Resists chemicals

Packaging:

UPC Code	043281004831
Cans per case	4
Container	1 gallon can (3.8 LITERS)
Shipping Classification	ORM-D, UN 1263
Hazard Class	3
Flammability	WARNING! Flammable liquid and vapor

Properties:

Coverage	Up to 200 square feet
Cleanup	Paint/lacquer thinner
Flash point	55F
Solids Content	79%
Zinc in dried paint film	86.3%
VOC content	235 g/l
HAPS Content	0%
Storage Temperature	40-100F
Application Temperature	50-90F
Durability	Excellent
Abrasion Resistance	Excellent
Heat Resistance	350F
Resin System	Modified epoxy
Density	18.9 pounds per gallon
Shelf life	1 year
Food contact rating	Category 21: Acceptable for incidental food contact.

Dry Time*:

To touch	10 minutes
To recoat	24 hours

*At 72F, 50% humidity, 1.5 mil thickness

Curing/Recoat time is extended with multiple coats and excessively thick coats

Gloss*: Flat, <5

*as measured on a 60 degree gloss meter

12-20-2019